

## Scanner Skyscan Microtomography with Temporary Teeth

\*Dr. Dobrinka Damyanova Phd<sup>1</sup>

<sup>1</sup>assistant Professor, Medical University - Varna, Bulgaria, Faculty Of Dental Medicine, Department Of Pediatric Dental Medicine Bulgaria

Corresponding author: \*Dr Dobrinka Damyanova Phd

---

### Abstract

**Purpose:** To monitor the changes in tooth enamel morphology under in vitro conditions after caries development and its treatment with a mineralization varnish - Clinpro™ White Varnish with TCP (3M).

**Methods:** The material used is from 20 temporary teeth. Treatment caries with remineralization with application of varnish - Clinpro™ White Varnish with TCP. The measurement was done with a desktop X-ray microtomography scanner SkyScan 1272 produced by the company Bruker. The experiment is conducted and captured six examiners from the Institute of Physical Chemistry,, Academic Rostislav Kaishev "of the Bulgarian Academy of Sciences in the city Sofia.

**Results:** Clearly differed are two areas; a lighter one, i. e. denser, which is on the outside – the tooth enamel, and a darker one – from the inner side of the tooth – dentin. These two areas are visible on all transverse (software) sections. The enamel thickness of a test sample varies between 300 and 500 μm. Monitoring of the area with dental caries, darker areas of enamel.

### Conclusion:

CT has observations that result in such a direction that the tooth surface is uneven as there are areas with varying degrees of unevenness.

**Keywords:** remineralization, mineralization varnish, CT- computer tomography

---

### I. Introduction

Correction in behavior helps self oral environment and prevent the development of carious lesions. There are methods for non-operative and operative preventive treatment requiring changes to the protocol for the treatment of caries in deciduous teeth [1,6].


**Purpose:** To monitor the changes in tooth enamel morphology under in vitro conditions after caries development and its treatment with a mineralization varnish - Clinpro™ White Varnish with TCP (3M).

### II. Materials And Methods

The material used is from 20 temporary intact teeth, extracted due to physiological change with permanent teeth, with a completely preserved structure and anatomy of crowns and fully physiologically resorbed roots. Then the samples are washed and dried with water and airflow. Treatment with remineralization with application of varnish - Clinpro™ White Varnish with TCP (Tri-Calcium phosphate) (3M). The experiment is conducted and captured six examiners from the Institute of Physical Chemistry,, Academic Rostislav Kaishev "of the Bulgarian Academy of Sciences in the city Sofia. The measurement is done with desktop X-ray mikrotomograf SkyScan 1272 produced by the company Bruker. Used X-ray tube voltage of 70 kV is, a magnitude of the current 142 μA, supplied as a 0.5 mm Al filter. The radiation is of conical shape. The increase is 13.45 times the size of a single voxel (3D pixel) - 0.55 μm. The measurement time is 13h: 44m: 49s. Reconstruction of 3D images includes the following adjustments: adjustment for fine / thermal displacement of the sample; correction amending the spectrum of radiation (beam hardening) and adjustment disorders circular (ring artifacts). The time for reconstruction is 1193 seconds.

### III. Results


At first glance there is no evidence of additional mineral layer on the surface of the tooth. This could mean several things: 1 on the tooth no additional coverage, 2 coating is very thin, in the 1-2 μm and / or a density that is very similar to that of enamel. The demand of the crystals of the layer remineralizes possible in size of the crystals above 50 μm and only on the surface. Representative images of the observed tooth sample are shown in Figure 1 et Figure 2.



**Figure 1.**

**Tomography of the deciduous tooth enamel- inner surface of the enamel to the enamel-dentin border (presence of two microcavitated caries lesions in the enamel)**


Figure 2 shows the outer surface of the tooth on which there are visible specific roughness.



**Figure 2.**

**Microtomography-cross-section of the deciduous tooth enamel. Outer surface of a deciduous tooth. The thickness of the enamel in the presented sample varies between 300 and 500  $\mu\text{m}$**

Clearly differed are two areas; a lighter one, i. e. denser, which is on the outside – the tooth enamel, and a darker one – from the inner side of the tooth – dentin. These two areas are visible on all transverse (software) sections. The enamel thickness of a test sample varies between 300 and 500  $\mu\text{m}$ . There are noticeable defects on the tooth enamel, which represent dark areas, i.e. areas of reduced density. Such areas in the depth of the enamel are presented in Figure 2 and 3 and Figure 4, clearly shows their volumetric nature.



**Figure 3**

### Volumetric section of a part of the enamel “body of the carious lesion” by dental caries - dark areas of reduced density




Figure 4

Over the “body of the carious lesion” part of the enamel layer there appears of a thickness of 10-14  $\mu\text{m}$ , which has a density similar to that of the healthy tooth enamel or even slightly higher. The same is shown in the cut in the figure, which is colored so that the higher density are is blue and the enamel caries defect is in yellow-green. Characterization of the roughness on the surface of the enamel in Figure 2 shows a height of between 6 and 14  $\mu\text{m}$  and a horizontal size of 14-40  $\mu\text{m}$ . At these sizes of possible crystals faceting can not be observed at the current resolution, which is determined by the focal spot of the X-ray tube -  $\sim 5 \mu\text{m}$ . The sharp crystal edges are smoothed as the CT image is a convolution of the research object and of the intensity profile of the focal spot. However, the study does not reject the possibility that these irregularities had a crystalline appearance. Figure 2 makes it also noticeable that this type of unevennesses is different in different parts of the surface. In the foreground there is an area with more and larger unevenness, while in the background and on the right there are smoother areas. This suggests that if there is some coverage, it is uneven on the surface and may even be missing somewhere. Perhaps this could be established by a comparative testing of the unvarnished part of the same tooth.

Monitoring of the area with “body of the carious lesion” of dental caries, darker areas of enamel in Figure 3 show that the larger of the two, which is located closer to the tooth surface in fact does not go out of it. It is covered by a layer with a thickness between 10 and 14  $\mu\text{m}$ , whose density is very close, and perhaps a bit higher than that of tooth enamel. It could be assumed that this is an effect of amending the spectrum of the beam as the correction for this effect can only be done for one of the phases in the sample; in this case the enamel has been selected. However, this hypothesis should be rejected because the difference in density between the damaged and the healthy part of the enamel is much smaller than that between the enamel and the dentin, and concerning the dentin effects from the spectrum change of the beam are not observed. Meanwhile, the subsequent images in Figure 4 show that a layer of approximately the same thickness 10-14  $\mu\text{m}$  has emerged upon incision of the sample. The size of 10-14  $\mu\text{m}$  is very close to the height of the irregularities observed on the surface of the tooth. These structures can be fluorapatite crystals.

#### IV. Discussion

Study correspond to higher fluoride retention after washing and moistening of the samples. Samples pass through a period of re-mineralization, deposition of calcium and phosphate ions from the varnish application [Culity BD, Stock SR, 2001,4,5]. This deposition can saturate the microstructures in enamel, making it more resistant to demineralization. When there is an acidic threat, enamel samples lined with varnish are able to be more resistant than the enamel of the deciduous teeth without the temporary application of a ternary fluoride varnish. Applied varnish material was tightly adherent, dry pressed to the deciduous tooth enamel sample, so long as it released fluoride for a longer period of time [2,3,8]. The enamel of deciduous teeth without application could not have been or be able to compensate for the loss of minerals. The caries lesion part of the enamel, however, is located in a smooth region on the surface [3,7,9,10,11].

#### V. Conclusions

1. In the uneven areas, their height, potentially that of the crystals from remineralizing coverage is between 6 and 14  $\mu\text{m}$ , with a horizontal size 14-40  $\mu\text{m}$ .
2. In the tooth enamel monitor an area is observed that is “sealed” with a layer of a density close to that of healthy dental enamel and a thickness of 10-14  $\mu\text{m}$ . In cutting of a sample such layer has also emerged on its surface. This leads to the hypothesis of the presence of the enamel coating layer whose density is very similar to that of the enamel.

### References

- [1]. Makinen KK. Sugar alcohols, caries incidence and remineralization of caries lesions: a literature review. *Int J Dent.* 2010; 2010:981072 [[PubMed](#)] [[CrossRef](#)].
- [2]. Walsh LJ. Evidence that demands a verdict: latest developments in remineralization therapies. *Aust Dent Pract.* 2009 Mar/Apr;20(2):48 -59.
- [3]. Iimima Y. Early detection of white spot lesions with digital camera and remineralization therapy. *Aust Dent J.* 2008 Sep;53(3):274-280 [[PubMed](#)] [[CrossRef](#)].
- [4]. Culity BD, Stock SR. Elements of X-ray dymation, 3<sup>rd</sup> ed. Upper saddle river, New Jersey: Prentice Hall. 2001.
- [5]. Gudavarthy Rakesh, Elizabeth A. Kulp. Epitaxial Electrodeposition of chiral films Using chiral precursors. Recent advances in cristalography: 1-20.
- [6]. Frencken JE, Holmgren CJ. Atraumatic Restorativ Treatment for Dental Caries. STI Book b.v. Nijmegen. 1999.
- [7]. Chou R, Cantor A, Zakher B, Mitchell JP, Pappas M. Preventing dental caries in Children, 5 years: Systemic review updating USPSTF recommendation. *Pediatrics.* 2013; 132(2): 332-35.
- [8]. Divaris K, Preisser JS, Slade GD. Surface-Specific Efficacy of Fluorde varnish in caries Prevention in the Primary dentition: Rezults of a Community Randomized clinical trial. *Caries Res.* 2013;47:78-87.
- [9]. Fejerskov O, Nyvad B, Kidd E. Dental caries: The Disease and its Clinical Management, 3<sup>rd</sup> Edition. Wiley-Blackwell. 2015:260-272.
- [10]. Austin RS, Stenhagen KS, Hove LH, Dunne S, Moazzez R, Bartlett DW. A qualitative and qualitative investigation into the effect of fluoride formations on enamel erosion and erosion-abrasion in vitro. *A. B. Tveit-Journal of dentistry.* 2011; 39:648-655.
- [11]. Gateva N, Kabaktchieva R. Dentin changes after demineralization and Deproteinization in both dentitions – SEM evaluation. *Dental Medicine.* 2014; 1:3-10.

\*Dr. Dobrinka Damyanova Phd1. "Scanner Skyscan Microtomography with Temporary Teeth."  
IOSR Journal of Dental and Medical Sciences (IOSR-JDMS) 16.7 (2017): 92-95.