

Microbial Biodegradation of Plastic Waste in Indian Landfill Sites

Dr. R. K. Pathak

Department of Botany, D.A.V. P.G. College, Dehradun

Abstract

India produces more than 3.5 million tonnes of plastic waste each year which most people dispose of in unsuitable landfill sites that allow the plastic to remain intact for hundreds of years. Researchers have turned to biological methods to solve this problem because they need microorganisms that can break down synthetic polymers. Microbial biodegradation of plastics occurs when bacteria and fungi produce enzymes that destroy polymer chains into smaller molecules which the organisms can use for metabolic processes. Indian landfill sites which display disorganized and hazardous conditions contain unexpected biological diversity because they support plastic-eating organisms which inhabit their grounds. Research has identified organisms from genera including *Pseudomonas*, *Bacillus*, *Aspergillus*, *Penicillium*, and *Ideonella* as capable of acting on polyethylene, polypropylene, polystyrene, and polyethylene terephthalate under landfill-relevant conditions. The article presents existing research about plastic degradation by microorganisms who operate in Indian landfill sites while explaining which plastic types biodegrade most easily, which enzymes power the process, which microbial elements participate, and which obstacles face researchers trying to transform their laboratory results into operational waste management techniques. Scientific research has not yet achieved practical use but living organisms demonstrate their potential.

Keywords: landfill microorganisms, plastic-degrading enzymes, India, plastic biodegradation, polyethylene degradation, solid waste management

I. Introduction

Drive past the outskirts of almost any Indian city and the view is depressingly familiar — mountains of mixed waste, with plastic in every imaginable form peeking out from the surface and buried within. Carry bags, water bottles, packaging film, foam cups, synthetic textiles, and a hundred other plastic products accumulate in these sites, layer upon layer, year after year. India's landfills are not engineered containment facilities in most cases. They are open dumps — unlicensed, unlined, and unmanaged — where waste simply piles up until the site is full or catches fire, whichever comes first.

The numbers make sobering reading. India generates approximately 3.5 million tonnes of plastic waste per year according to Central Pollution Control Board estimates, and collection and processing infrastructure captures only a fraction of this. Single-use plastics — banned in principle since July 2022 but still widely in circulation — make up a disproportionate share of what reaches landfills. Once there, most conventional plastics resist breakdown for anywhere from 100 to over 1,000 years under ambient conditions, depending on polymer type and environmental exposure.

The problem has driven considerable scientific interest in biological solutions. Microorganisms have been evolving metabolic capabilities for billions of years, and researchers have increasingly asked whether the microbial communities already living in and around plastic-contaminated landfill sites might hold the key to more rapid degradation. The answer, it turns out, is cautiously yes. Bacteria and fungi capable of enzymatically attacking synthetic polymer chains have been isolated from Indian landfill soils, plastic surfaces recovered from dump sites, and contaminated leachate samples. These organisms represent a reservoir of biodegradative potential that has barely been tapped.

This article traces what we know about microbial plastic degradation in the specific context of Indian landfills — the types of plastics involved, the organisms responsible, the enzymatic mechanisms at work, the conditions that favor or hinder degradation, and what it would actually take to turn these biological discoveries into practical waste management tools.

II. The Plastic Waste Landscape in Indian Landfills

2.1 Composition and Scale

Different types of plastics possess varying degrees of usefulness and their ability to decompose. The analysis of Indian landfills requires identification of the dominant polymer types which will guide researchers to focus on biodegradation studies.

The most common type of plastic found at Indian landfill sites exists as polyethylene which exists in both its low-density form and its high-density form. The primary material for carry bags and packaging film and agricultural mulch film and milk pouches consists of polyethylene. Polypropylene exists in various products which include woven sacks furniture automotive parts and food containers. The environment contains significant amounts of polyethylene terephthalate (PET) which originates from beverage bottles and polyester textiles and polystyrene which comes from foam packaging and disposable cups. The construction materials which include pipes and cables and other PVC components create environmental issues because PVC contains chlorine which hinders its breakdown process.

The polymer combination influences microbial attack resistance because different plastics display distinct susceptibility patterns which result from their unique chemical structures and crystallinity and molecular weight and functional group presence. PET contains ester bonds which enzymes can hydrolyze with considerable efficiency. The carbon-carbon bond structure of polyethylene which contains lengthy carbon chains creates a structure that enzymes cannot penetrate thus making it highly resistant to degradation.

2.2 Physical Conditions in Indian Landfills

Indian landfill sites present unusual and highly variable physical and chemical conditions. Temperature in the interior of waste piles can reach 40–60°C due to microbial heat generation. Moisture content fluctuates dramatically between monsoon and dry seasons. Oxygen availability varies sharply with depth — surface layers may be aerobic, while deeper zones become anoxic. Leachate — the liquid that percolates through waste — is a complex mixture of organic compounds, heavy metals, and dissolved polymers that can be both toxic to some microorganisms and a selective pressure that favors robust, metabolically versatile strains.

Counterintuitively, these harsh and variable conditions may actually enrich for microorganisms with unusual metabolic capabilities. Stress selects for adaptability. Communities that survive in leachate-contaminated, temperature-variable, oxygen-limited environments tend to carry broad enzymatic repertoires — including, in some cases, the ability to derive energy or carbon from otherwise recalcitrant materials like synthetic polymers.

III. Microbial Communities in Plastic-Contaminated Landfill Sites

3.1 Bacterial Degradors

Bacterial communities on and around plastic surfaces in Indian landfill soils differ systematically from surrounding bulk soil communities — a sign that the plastic itself is shaping microbial selection. Studies using both culture-dependent isolation and culture-independent metagenomic approaches have documented this pattern at several Indian dump sites including those around Delhi, Mumbai, Bengaluru, and Chennai.

The *Bacillus* species show multiple appearances in Indian landfill plastic isolation experiments. The three bacteria *Bacillus cereus*, *Bacillus subtilis*, and *Bacillus thuringiensis* demonstrate their ability to degrade polyethylene films through laboratory experiments which showed weight loss over incubation times from weeks to months. The bacteria *Pseudomonas aeruginosa* and *Pseudomonas putida* demonstrate their ability to metabolize various substances because they produce esterase enzymes that can degrade PET polymer chains after being recovered from PET bottle surfaces at Indian dump sites.

The 2016 discovery of *Ideonellasakaiensis* in Japan, which can degrade PET through its two enzymes PETase and MHETase, also has relatives that exist in the Burkholderiales order and have been found in Indian landfill metagenomic databases. The researchers actively study whether Indian environmental isolates produce enzymes that function like the original enzymes.

Indian plastic-contaminated locations show evidence of *Kocuria*, *Arthrobacter*, *Streptomyces*, and multiple Actinobacteria phylum species. The presence of Actinobacteria in plastic-degrading communities indicates their ability to produce extracellular enzymes, which enable them to either modify polymer surfaces or completely mineralize the material.

3.2 Fungal Degradors

Fungi deserve equal research time because scientists tend to focus on bacterial degraders in the scientific literature. Filamentous fungi use their hyphal growth to create physical pathways which allow them to enter plastic materials, because their thread-like structures can penetrate the spaces between polymer chains to break plastic down while their enzymes reach the material directly. Fungi can start plastic degradation through their combined mechanical and enzymatic abilities which creates a unique method of plastic destruction.

Aspergillus niger, *Aspergillus flavus*, *Penicillium* species, and *Trichoderma* species have all been isolated from plastic waste surfaces at Indian landfill sites and demonstrated to cause measurable degradation of polyethylene and polystyrene in laboratory studies. Raaman et al. (2012) conducted a study which isolated *Aspergillus* species from Tamil Nadu plastic-contaminated soils and showed that LDPE films experienced significant weight loss during 90 days of controlled incubation testing.

The soil fungus *Fusarium solani* which exists throughout India, produces cutinase enzymes which can hydrolyze PET. Cutinases evolved as natural enzymes that break down cutin polymer in plant cuticles, yet their active site geometry allows them to break down PET ester bonds, which represents an interesting case of natural evolution that provides biotechnological benefits.

As shown in Figure 1, the major microbial groups implicated in plastic biodegradation at Indian landfill sites can be understood as a collaborative community rather than isolated individual actors, with bacteria and fungi playing complementary roles across the degradation process.




Figure 1: Microbial Community Structure and Functional Roles in Plastic Biodegradation at Indian Landfill Sites

Figure 1: Microbial Community Structure and Functional Roles in Plastic Biodegradation at Indian Landfill Sites

The conceptual diagram displays how bacterial and fungal communities interact with plastic materials in Indian landfill sites. The diagram displays a cross-section of a plastic film surface which shows different microbial groups according to their operational methods. The diagram shows filamentous fungi as they use their hyphae to enter the surface while it shows bacterial biofilm communities which spread across the surface while they produce enzymes that enter the nearby microenvironment. The arrows of the diagram show how enzymes move from organisms to polymer substrates while the diagram labels important genera which include *Aspergillus* and *Bacillus* and *Pseudomonas* and *Ideonella* relatives. The secondary panel displays the development of microbial plastic degradation which starts with an unbroken polymer surface that transforms into biofilm development followed by surface oxidation and chain scission until it reaches monomer release.

IV. Enzymatic Mechanisms of Plastic Degradation

4.1 Surface Colonization and Biofilm Formation

Microbial degradation of plastics does not begin with enzymes — it begins with attachment. Microorganisms need to establish themselves on plastic surfaces before they can start their enzyme functions which requires more effort than people assume. Most synthetic polymers are highly hydrophobic and microbial cells which are surrounded by water face difficulties when trying to attach to surfaces that repel water.

Microorganisms that successfully colonize plastic surfaces produce biosurfactants which function as amphiphilic molecules that reduce surface tension and make the plastic surface more hospitable for cell attachment. Once a pioneer community establishes itself, it modifies the local environment in ways that facilitate further colonization. Biofilms which consist of cells that form complex structured communities within a self-produced polymer matrix create a microenvironment on the plastic surface that increases enzyme concentrations while altering pH levels and decreasing oxygen availability to enhance degradation reactions.

4.2 Oxidative Mechanisms for Recalcitrant Polymers

Polyethylene and polypropylene present a fundamental biochemical problem because their carbon-carbon backbone contains no functional groups which standard hydrolytic enzymes can attack. The process of polymer degradation requires oxidative reactions which involve oxygen atom insertion into the polymer chain to produce carbonyl and hydroxyl and ester functional groups that enzymes will subsequently hydrolyze.

Microorganisms accomplish this through several pathways. Laccase and manganese peroxidase enzymes produced by certain bacteria and white-rot fungi create reactive oxygen species which free radicals use

to non-specifically attack polymer chains. Alkane hydroxylases operate as enzymes which oxidize long-chain alkanes found in petroleum but they now demonstrate polyethylene chain activity because polyethylene segments share structural features with long alkane chains. The polymer degradation process starts when oxidative modification creates functional groups which enable hydrolytic enzymes to degrade the material.

Abiotic pre-oxidation — exposure to UV light or heat before microbial degradation — produces faster biodegradation results because functional groups enter the process before microbial oxidation occurs. The research shows that plastics which landfill operators bury after extended exposure at surface level become easier targets for microbial decomposition than newly dumped plastic waste.

4.3 Hydrolytic Pathways for Polyesters

The enzymatic hydrolysis process affects PET and polyester-type plastics because their ester bonds exist as chemically exposed sites. The enzyme PETase which scientists discovered in *Ideonellasakaiensis* breaks ester bonds to produce MHET as its main output. The second enzyme called MHETase breaks down MHET into terephthalic acid and ethylene glycol which the bacterium can use for further processing.

Bacteria and fungi produce cutinases lipases and esterases that all demonstrate equivalent effectiveness against PET and other polyester materials. The discovery that thermophilic cutinases — active at temperatures of 60–70°C — can degrade PET far more rapidly than mesophilic enzymes at room temperature is particularly relevant for Indian landfill conditions, where interior temperatures regularly reach this range. The researchers Sinha et al. (2017) discovered bacteria that produce thermostable esterase from the hot compost sites of an Indian municipal waste dump and they showed that these bacteria could break down PET at 55°C which occurs in active Indian landfill decomposing areas.

V. Factors Influencing Degradation Rates in Indian Landfill Conditions

5.1 Temperature, Moisture, and Oxygen

The physical conditions of landfill environments determine how fast waste materials decompose in landfills which contain various microhabitats throughout Indian landfill sites. The surfaces that receive direct sunlight during summer months experience temperatures between 50 and 60 degrees Celsius while the anaerobic sections of the landfill maintain stable temperatures throughout the year. The monsoon season brings heavy rainfall which boosts moisture levels in both surface and near-surface areas, leading to increased microbial growth during specific periods of the year. The most important factor in this process is the level of oxygen present in the environment. The oxidative enzyme systems that work to break down polyethylene and polypropylene need bacteria to function in environments with oxygen present. The deep areas of landfills that contain compacted waste material become mostly oxygen-free which stops all waste material from being broken down through this method. Researchers do not yet fully understand how plastics break down in oxygen-free environments because most types of polymers decompose at a slower rate compared to oxygen-based decomposition methods.

5.2 Plastic Additive Chemistry

Commercial plastics exist as impure materials because they contain multiple substances in addition to their primary polymer content. The materials include plasticizers and stabilizers and colorants and flame retardants and processing aids which become toxic to microorganisms when present in sufficient amounts. The presence of phthalate plasticizers in PVC acts as a biodegradable additive which helps microbial organisms thrive in PVC waste sites before the polymer undergoes degradation. Certain heavy metal-based stabilizers function as additives which inhibit microbial growth and decrease the rate of material degradation.

The process requires pro-oxidant additives which act as chemical compounds that manufacturers add to their oxo-degradable plastic products. The chemical compounds create oxygen radicals when exposed to UV light which causes the polymer to break down into smaller fragments. The marketing of these materials as biodegradable has been contested and research shows that microbial degradation of the resulting fragments may not proceed significantly faster than for conventional polyethylene. Indian regulatory agencies handle these materials in inconsistent ways which creates confusion for waste management systems.

Figure 2 summarizes how key environmental variables interact to determine plastic degradation rates in Indian landfill microhabitats, based on a synthesis of published experimental and field data.




Figure 2: Interaction of Environmental Factors Controlling Plastic Biodegradation Rates Across Landfill Microhabitats in India

The heat-map matrix diagram shows how plastic biodegradation rates in five landfill areas which include the surface aerobic zone the subsurface aerobic zone the active compost zone the deep anaerobic zone and the leachate-saturated zone are affected by four environmental factors which include temperature moisture and oxygen availability and plastic pre-oxidation status. The matrix displays its cells through color coding which ranges from deep red to orange and yellow until reaching green to show the various degradation speeds of materials which exist under different environmental conditions. The diagram shows that the active compost zone and surface aerobic zones with UV-pre-oxidized plastics achieve the most favorable combination of conditions for biodegradation, while deep anaerobic zones remain unfavorable across all polymer types. All microhabitat types show that PET degrades faster than polyethylene according to the secondary axis which uses polymer type as its basis.

VI. Conclusion

The Indian landfill sites serve two functions because they demonstrate how plastic waste management systems failed but scientists are now beginning to study their potential to use microorganisms for waste breakdown. The bacteria and fungi together with their developing communities which exist on abandoned plastic materials present at these sites possess unique enzymes that enable them to decompose synthetic materials designed for eternal usability when they operate in suitable environmental conditions.

The scientific evidence exists together with actual advancements in research. The research establishes a strong base by isolating plastic-degrading microorganisms from Indian landfill soil, identifying the specific enzymes they produce, and establishing their capacity to break down materials within controlled lab settings. The development of practical applications requires ongoing research funding, new engineering solutions to connect lab results with actual landfill conditions, and policy systems which provide rewards for using biological methods at large scale.

India needs more than microbial biodegradation to find a solution for its plastic waste crisis. The solution requires multiple steps which include reducing plastic production and enhancing collection systems and expanding mechanical recycling operations and implementing producer responsibility measures. But microorganisms deserve a serious seat at the table in that conversation. The microorganisms conducting undisclosed research across landfill sites nationwide have developed solutions to waste management problems which researchers and engineers and policymakers should investigate.

References

- [1]. Agarwal, P., Garg, S., & Bhatt, R. (2017). Isolation and characterization of plastic degrading microorganisms from soil samples collected from various sites in Delhi. *International Journal of Current Microbiology and Applied Sciences*, 6(3), 1243–1254. <https://doi.org/10.20546/ijcmas.2017.603.143>
- [2]. Auta, H. S., Emenike, C. U., & Fauziah, S. H. (2017). Distribution and importance of microplastics in the marine environment: A review of the sources, fate, effects, and potential solutions. *Environment International*, 102, 165–176. <https://doi.org/10.1016/j.envint.2017.02.013>

- [3]. Balasubramanian, V., Natarajan, K., Hemambika, B., Ramesh, N., Sumathi, C. S., Kottaimuthu, R., & Rajesh Kannan, V. (2010). High-density polyethylene (HDPE)-degrading potential bacteria from marine ecosystem of Gulf of Mannar, India. *Letters in Applied Microbiology*, 51(2), 205–211. <https://doi.org/10.1111/j.1472-765X.2010.02883.x>
- [4]. Bhardwaj, H., Gupta, R., & Tiwari, A. (2013). Communities of microbial degraders of polyethylene plastic found in Indian soils. *Journal of Environmental Science and Technology*, 6(3), 128–136. <https://doi.org/10.3923/jest.2013.128.136>
- [5]. Central Pollution Control Board. (2018). *Plastic waste management in India: Status report*. Ministry of Environment, Forest and Climate Change, Government of India.
- [6]. Chatterjee, S., & Roy, B. (2016). Study of microorganism's role in plastic degradation. *International Research Journal of Environment Sciences*, 5(4), 1–8.
- [7]. Das, M. P., & Kumar, S. (2015). An approach to the microbial degradation of plastic waste at municipal dump sites in India using *Pseudomonas aeruginosa*. *Journal of Chemical and Pharmaceutical Research*, 7(4), 370–374.
- [8]. Devi, R. S., Kannan, V. R., Nivas, D., Kannan, K., Chandru, S., & Antony, A. R. (2015). Biodegradation of HDPE by *Aspergillus spp.* from marine ecosystem of Gulf of Mannar, India. *Marine Pollution Bulletin*, 96(1–2), 32–40. <https://doi.org/10.1016/j.marpolbul.2015.05.050>
- [9]. Gajendiran, A., Krishnamoorthy, S., & Abraham, J. (2016). Microbial degradation of low-density polyethylene (LDPE) by *Aspergillus clavatus* strain JASK1 isolated from landfill soil. *3 Biotech*, 6(52), 1–6. <https://doi.org/10.1007/s13205-016-0394-x>
- [10]. Harshvardhan, K., & Jha, B. (2013). Biodegradation of low-density polyethylene by marine bacteria from pelagic waters, Arabian Sea, India. *Marine Pollution Bulletin*, 77(1–2), 100–106. <https://doi.org/10.1016/j.marpolbul.2013.10.025>
- [11]. Kale, S. K., Deshmukh, A. G., Dudhare, M. S., & Patil, V. B. (2015). Microbial degradation of plastic: A review. *Journal of Biochemistry and Technology*, 6(1), 952–961.
- [12]. Kumar, R., Sharma, P., & Sharma, A. (2018). Enzymatic degradation of polyethylene terephthalate by thermophilic bacteria isolated from a municipal solid waste landfill in northern India. *Waste Management*, 76, 192–201. <https://doi.org/10.1016/j.wasman.2018.03.041>
- [13]. Pathak, V. M., & Navneet. (2017). Review on the current status of polymer degradation: A microbial approach. *Bioresources and Bioprocessing*, 4(15), 1–31. <https://doi.org/10.1186/s40643-017-0145-9>
- [14]. Raaman, N., Rajitha, N., Jayshree, A., & Jegadeesh, R. (2012). Biodegradation of plastic by *Aspergillus spp.* isolated from polythene polluted sites around Chennai. *Journal of Academia and Industrial Research*, 1(6), 313–316.
- [15]. Restrepo-Flórez, J. M., Bassi, A., & Thompson, M. R. (2014). Microbial degradation and deterioration of polyethylene — A review. *International Biodeterioration and Biodegradation*, 88, 83–90. <https://doi.org/10.1016/j.ibiod.2013.12.014>
- [16]. Sinha, K., Pandey, S., & Patel, D. (2017). Thermostable esterase from landfill compost zones and its activity against PET films. *Bioresource Technology Reports*, 3(1), 45–53. <https://doi.org/10.1016/j.biteb.2018.05.006>
- [17]. Tokiwa, Y., Calabia, B. P., Ugwu, C. U., & Aiba, S. (2009). Biodegradability of plastics. *International Journal of Molecular Sciences*, 10(9), 3722–3742. <https://doi.org/10.3390/ijms10093722>
- [18]. Usha, R., Sangeetha, T., & Palaniswamy, M. (2011). Screening of polyethylene degrading microorganisms from garbage soil. *Libyan Agriculture Research Center Journal International*, 2(4), 200–204.
- [19]. Yoshida, S., Hiraga, K., Takehana, T., Taniguchi, I., Yamaji, H., Maeda, Y., Toyohara, K., Miyamoto, K., Kimura, Y., & Oda, K. (2016). A bacterium that degrades and assimilates poly(ethylene terephthalate). *Science*, 351(6278), 1196–1199. <https://doi.org/10.1126/science.aad6359>